

Alumina(Al₂O₃)- -Inch Size



パート 番号	Grade	最大 温度(℃)	Density	硬 度(HRC)	ボール・ ダイヤ耐 性	Sphericity	Weight	Material	熱膨張の 係数 α (10 ⁻⁶ /K)	ポア ソン 比	計測シ ステム	RoHS	REACH
2"	G10	1800	3.95 g/cm	80	0.000010"	0.000010"	268.39g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
1 7/8"	G10	1800	3.95 g/cm	80	0.000010"	0.000010"	221.15g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
1 3/8"	G10	1800	3.95 g/cm	80	0.000010"	0.000010"	87.21g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
1 1/2"	G10	1800	3.95 g/cm	80	0.000010"	0.000010"	113.23g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
1 1/16"	G10	1800	3.95 g/cm	80	0.000010"	0.							

Alumina(Al₂O₃)- -Inch Size

21/32"	G10	1800	3.108 g/cm	80	0.000010"	0.000010"	9.482g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
5/8"	G10	1800	3.109 g/cm	80	0.000010"	0.000010"	8.191g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
19/32"	G10	1800	3.110 g/cm	80	0.000010"	0.000010"	7.022g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
9/16"	G10	1800	3.111 g/cm	80	0.000010"	0.000010"	5.972g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
17/32"	G10	1800	3.112 g/cm	80	0.000010"	0.000010"	5.03g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
1/2"	G10	1800	3.113 g/cm	80	0.000010"	0.000010"	4.194g	Alumina(Al ₂ O ₃)	9.1	0.27	Imperial	YES	YES
31/64													