

Stainless Steel Balls



| 製品番号                                  | ボール直径 | Material             | 直径許容範囲                | Hardness | 最高気温           | Grade | MOQ  | Package | Certificate | Color   |
|---------------------------------------|-------|----------------------|-----------------------|----------|----------------|-------|------|---------|-------------|---------|
| AISI 440C Stainless Steel Balls 24 mm | 24 mm | 440C Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65 | 800° F   427°C | G10   | 1PCS | Stadard | Rohs        | silvery |
| AISI 440C Stainless Steel Balls 18 mm | 18 mm | 440C Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65 | 800° F   427°C | G10   | 1PCS | Stadard | Rohs        | silvery |
| AISI 440C Stainless Steel Balls 16 mm | 16 mm | 440C Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65 | 800° F   427°C | G10   | 1PCS | Stadard | Rohs        | silvery |
| AISI 440C Stainless Steel Balls 15 mm | 15 mm | 440C Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65 | 800° F   427°C | G10   | 1PCS | Stadard | Rohs        | silvery |
| AISI 440C Stainless Steel Balls 14 mm | 14 mm | 440C Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65 | 800° F   427°C | G10   | 1PCS | Stadard | Rohs        | silvery |
| AISI 440C Stainless Steel Balls 13 mm | 13 mm | 440C Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65 | 800° F   427°C | G10   | 1PCS | Stadard | Rohs        | silvery |

## Stainless Steel Balls

|                                             |       |                         |                       |                     |                |     |      |         |      |         |
|---------------------------------------------|-------|-------------------------|-----------------------|---------------------|----------------|-----|------|---------|------|---------|
| AISI 440C<br>Stainless Steel<br>Balls 12 mm | 12 mm | 440C<br>Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65            | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 316L<br>Stainless Steel<br>Balls 12 mm | 12 mm | 316L<br>Stainless Steel | -0.013mm to 0.013mm   | Rockwell B90        | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 304<br>Stainless Steel<br>Balls 12 mm  | 12 mm | 304<br>Stainless Steel  | -0.0127mm to 0.0127mm | Rockwell C25 (Hard) | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 440C<br>Stainless Steel<br>Balls 10 mm | 10 mm | 440C<br>Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65            | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 316L<br>Stainless Steel<br>Balls 10 mm | 10 mm | 316L<br>Stainless Steel | -0.013mm to 0.013mm   | Rockwell B90        | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 304<br>Stainless Steel<br>Balls 10 mm  | 10 mm | 304<br>Stainless Steel  | -0.0127mm to 0.0127mm | Rockwell C25 (Hard) | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 440C<br>Stainless Steel<br>Balls 9 mm  | 9 mm  | 440C<br>Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65            | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 440C<br>Stainless Steel<br>Balls 8 mm  | 8 mm  | 440C<br>Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65            | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 316L<br>Stainless Steel<br>Balls 8 mm  | 8 mm  | 316L<br>Stainless Steel | -0.013mm to 0.013mm   | Rockwell B90        | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |

## Stainless Steel Balls

|                                                     |         |                            |                             |                           |                      |     |      |         |      |         |
|-----------------------------------------------------|---------|----------------------------|-----------------------------|---------------------------|----------------------|-----|------|---------|------|---------|
| AISI 304<br>Stainless<br>Steel<br>Balls 8<br>mm     | 8<br>mm | 304<br>Stainless<br>Steel  | -0.0127mm<br>to<br>0.0127mm | Rockwell<br>C25<br>(Hard) | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI<br>440C<br>Stainless<br>Steel<br>Balls 7<br>mm | 7<br>mm | 440C<br>Stainless<br>Steel | -0.0025mm<br>to<br>0.0025mm | HRC60-65                  | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI<br>316L<br>Stainless<br>Steel<br>Balls 7<br>mm | 7<br>mm | 316L<br>Stainless<br>Steel | -0.013mm<br>to<br>0.013mm   | Rockwell<br>B90           | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 304<br>Stainless<br>Steel<br>Balls 7<br>mm     | 7<br>mm | 304<br>Stainless<br>Steel  | -0.0127mm<br>to<br>0.0127mm | Rockwell<br>C25<br>(Hard) | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI<br>440C<br>Stainless<br>Steel<br>Balls 6<br>mm | 6<br>mm | 440C<br>Stainless<br>Steel | -0.0025mm<br>to<br>0.0025mm | HRC60-65                  | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI<br>316L<br>Stainless<br>Steel<br>Balls 6<br>mm | 6<br>mm | 316L<br>Stainless<br>Steel | -0.013mm<br>to<br>0.013mm   | Rockwell<br>B90           | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 304<br>Stainless<br>Steel<br>Balls 6<br>mm     | 6<br>mm | 304<br>Stainless<br>Steel  | -0.0127mm<br>to<br>0.0127mm | Rockwell<br>C25<br>(Hard) | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI<br>440C<br>Stainless<br>Steel<br>Balls 5<br>mm | 5<br>mm | 440C<br>Stainless<br>Steel | -0.0025mm<br>to<br>0.0025mm | HRC60-65                  | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI<br>316L<br>Stainless<br>Steel<br>Balls 5<br>mm | 5<br>mm | 316L<br>Stainless<br>Steel | -0.013mm<br>to<br>0.013mm   | Rockwell<br>B90           | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 304<br>Stainless<br>Steel<br>Balls 5<br>mm     | 5<br>mm | 304<br>Stainless<br>Steel  | -0.0127mm<br>to<br>0.0127mm | Rockwell<br>C25<br>(Hard) | 800°<br>F  <br>427°C | G10 | 1PCS | Stadard | Rohs | silvery |

## Stainless Steel Balls

|                                              |        |                         |                       |                     |                |     |      |         |      |         |
|----------------------------------------------|--------|-------------------------|-----------------------|---------------------|----------------|-----|------|---------|------|---------|
| AISI 440C<br>Stainless Steel<br>Balls 4 mm   | 4 mm   | 440C<br>Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65            | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 316L<br>Stainless Steel<br>Balls 4 mm   | 4 mm   | 316L<br>Stainless Steel | -0.013mm to 0.013mm   | Rockwell B90        | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 304<br>Stainless Steel<br>Balls 4 mm    | 4 mm   | 304<br>Stainless Steel  | -0.0127mm to 0.0127mm | Rockwell C25 (Hard) | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 440C<br>Stainless Steel<br>Balls 3.5 mm | 3.5 mm | 440C<br>Stainless Steel | -0.0025mm to 0.0025mm | HRC60-65            | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |
| AISI 316L<br>Stainless Steel<br>Balls 3.5 mm | 3.5 mm | 316L<br>Stainless Steel | -0.013mm to 0.013mm   | Rockwell B90        | 800° F   427°C | G10 | 1PCS | Stadard | Rohs | silvery |